

SEAM FELT FOR PAPERMAKING

Patent Number: JP11200275
Publication date: 1999-07-27
Inventor(s): HAGIWARA YASUYUKI
Applicant(s): ICHIKAWA WOOLEN TEXTILE CO LTD
Requested Patent: ☐ JP11200275
Application Number: JP19970367555 19971226
Priority Number(s):
IPC Classification: D21F7/10
EC Classification:
Equivalents:


Abstract

PROBLEM TO BE SOLVED: To obtain a seam felt for papermaking, capable of shortening effort and time required for joining and not producing seam mark to wet paper by improving engaging property between seam loops and realizing threadability of core line.


SOLUTION: In this seam felt for papermaking, using a woven fabric forming a seam loop 2 at both end parts as a base fabric, the seam loop 2 is defined within the range of loop length of 1.6 mm to 2.4 mm and inclination of loop is thermally set at perpendicular angle or an angle which is approximate to perpendicular angle to base level and improvement of engaging property between seam loops and ready threading of core line can be realized regardless of short loop length.

Data supplied from the esp@cenet database - I2


【図1】




【図2】



【図3】



【図4】



【図5】

